



biosil® industrial technique biosoluble mineral wool

PRODUCT CHARACTERISTICS

Loose wool, mats and cuttings based on **biosoluble mineral wool** for a good **acoustic absorption** and **thermal insulation**.

TECHNICAL CHARACTERISTICS

Material	biosoluble mineral wool	Resistance to acid (16% HCl / 23 °C / 10min) *	> 99,0 %
Colour	nature	(16% HCl / 23 °C / 240h) *	≥ 98,0 %
Transformation temperature (DIN ISO 7884-8)	654 °C	Fasionaire PA 001) *	130 - 150
Filament structure	glass (amorph)	Flammability (DIN 4102/Teil 4)	non-combustible A1 (loose wool)
Ignition loss (%) (PA 007-2; analogous to DIN / ISO 1887) *	2,5 – 4,5	Biopersistance (i.t.- test) **	< 40 days half life
Moisture content (PA 007-2; analogous to ISO 3344)	1 – 2 %	Shot content (PA 007-1) *	< 20%

CHEMICAL COMPOSITION	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃ total	MgO+CaO	K ₂ O+Na ₂ O	MnO					
Wt. - %	60,2 ± 2	1,1 ± 1	5,5 ± 1,5	28,1 ± 2	5,0 ± 1,5	≤ 1,1					
THERMAL CONDUCTIVITY λ (DIN 52612-2)	W/m*K	0,034	0,042	0,063	0,093	0,135	0,189	0,259			
(by density 120 kg/m ³)	°C	50	100	200	300	400	500	600			
ACOUSTIC ABSORPTION (DIN EN ISO 10534-2) (density 120 kg/m ³ , Fas. 65)											
Frequency (Hz)	100	125	160	200	250	315	400	500	630	800	1000
biosil-wool 100 kg/m ³	0,19	0,20	0,21	0,24	0,28	0,34	0,45	0,54	0,68	0,81	0,91

* DBW testing specifications

** intratrachialer test

The technical information provided to the current state of the technology and is accurate to the best of our knowledge.

DBW Advanced Fiber Technologies GmbH

Rodetal 40
37120 Bovenden
Deutschland

Technical contact person:

Matthias von Wensiersky
Tel. +49 (0)5594 801-16
matthias.wensiersky@dbw.de
www.dbw.de

Sales contact person:

Elena König
Tel. +49 (0)5594 801-40
elena.koenig@dbw.de
www.dbw.de