



biosil® PT6

biosoluble mineral wool

PRODUCT CHARACTERISTICS

Rolls, cuttings, pressed and moulded parts based on biosoluble mineral wool for a good **acoustic absorption** and **thermal insulation** for **Engine Compartment** (bonnet, tunnel and dash panel insulation).

TECHNICAL CHARACTERISTICS

Material	biosoluble mineral wool	Fasonaire	170 ± 30
Colour	nature	PA 001) *	
Transformation temperature (DIN ISO 7884-8)	654 °C	Biopersistance (i.t.- test) **	< 40 days half life
Filament structure	glass (amorph)	Burnrate (ISO 3795)	0 mm/min
Ignition loss (%) (PA 007-2; analogous to DIN / ISO 1887) *	6 ± 2	Shot content (PA 007-1) *	< 20%

CHEMICAL COMPOSITION

	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃ total	MgO+CaO	K ₂ O+Na ₂ O	MnO
Wt. - %	60,2 ± 2	1,1 ± 1	5,5 ± 1,5	28,1 ± 2	5,0 ± 1,5	≤ 1,1

THERMAL CONDUCTIVITY λ (DIN 52612-2)

	W/m*K	0,028	0,034	0,049	0,071	0,101	0,140
(mean temperature, , ρ= 110 kg/m ³ , Fas. 140)	°C	50	100	200	300	400	500

* DBW testing specifications

** intratrachialer test

The technical information provided to the current state of the technology and is accurate to the best of our knowledge.

DBW Advanced Fiber Technologies GmbH

Rodetal 40
37120 Bovenden
Deutschland

Technical contact person:

Matthias von Wensiersky
Tel. +49 (0)5594 801-16
matthias.wensiersky@dbw.de
www.dbw.de

Sales contact person:

Elena König
Tel. +49 (0)5594 801-40
elena.koenig@dbw.de
www.dbw.de