



powerfil® 1200

Textile glass fiber, direct roving

PRODUCT CHARACTERISTICS

For **weaving**, for **reinforcement of plastic** (compatible to polyester-, vinyl- and epoxy resins), as well as for the **thermal** and **acoustic insulation**.

TECHNICAL CHARACTERISTICS

Material	textile glass fiber (continuous)
Fiber structure	glass (amorph)
Filament diameter (ISO 1888)	17 and 19 µm
Softening temperature (DIN ISO 7884-5, analogous ASTM C338)	925 °C
Transformation temperature (DIN ISO 7884-8)	760 °C
Spezific density (ASTM D1505)	2,6 – 2,7 g/cm ³
Resistance to acid (16% HCl / 23 °C / 10 min.)*	≥ 99,0 %
Resistance to alkali (20% NaOH / 50 °C / 24h)*	≥ 90,0 %

	Nominal value	Tolerance	Test method
Linear Density, tex	1200	± 5%	DIN EN ISO 1889
Moisture content, %	-	max. 0,1	ISO 3344
Ignition loss, %	0,5%	±15%	ISO 1887

* DBW testing specifications

The technical information provided to the current state of the technology and is accurate to the best of our knowledge.

DBW Advanced Fiber Technologies GmbH

Rodetal 40
37120 Bovenden
Deutschland

Technical contact person:

Matthias von Wensiersky
Tel. +49 (0)5594 801-16
matthias.wensiersky@dbw.de
www.dbw.de

Sales contact person:

Claudia Mahrt
Tel. +49 (0)5594 801-766
claudia.mahrt@dbw.de
www.dbw.de