



## powerfil® 410

Textile glass fiber, direct roving

### PRODUCT CHARACTERISTICS

For **weaving, knitting**, for **reinforcement of plastic** (compatible to polyester-, vinyl- and epoxy resins), as well as for the **thermal and acoustic insulation**.

### TECHNICAL CHARACTERISTICS

<b>Material</b>	textile glass fiber (continuous)	<b>Linear density (ISO 1889)</b>	
		Nominal value	410 tex
		Tolerance	± 5%
<b>Fiber structure</b>	glass (amorph)	<b>Spezific density</b> (ASTM D1505)	2,6 – 2,7 g/cm <sup>3</sup>
<b>Filament diameter</b> (ISO 1888)	16 µm	<b>Resistance to acid</b> (16% HCl / 23 °C / 10 min.)*	≥ 99,0 %
<b>Softening temperature</b> (DIN ISO 7884-5, analogous ASTM C338)	925 °C	<b>Resistance to alkali</b> (20% NaOH / 50 °C / 24h)*	≥ 90,0 %
<b>Transformation temperature</b> (DIN ISO 7884-8)	760 °C		

\* DBW testing specifications

The technical information provided to the current state of the technology and is accurate to the best of our knowledge.

#### DBW Advanced Fiber Technologies GmbH

Rodetal 40  
37120 Bovenden  
Deutschland

#### Technical contact person:

Matthias von Wensiersky  
Tel. +49 (0)5594 801-16  
matthias.wensiersky@dbw.de  
www.dbw.de

#### Sales contact person:

Claudia Mahrt  
Tel. +49 (0)5594 801-766  
claudia.mahrt@dbw.de  
www.dbw.de